


MAY 16, 2005 12:33PM

OBLOM SPIVAK

NO. 981 P. 1



**FACSIMILE**

PLEASE CALL US AT (703) 413-3000 IF THE MESSAGE YOU RECEIVE IS INCOMPLETE OR NOT LEGIBLE

TO Examiner Bolden DATE May 16, 2005

NAME

USPTO

COMPANY/FIRM

NUMBER OF PAGES INCLUDING COVER: 3

FAX #

CONFIRM FAX: ☐ YES ☒ NO

FROM Kristen A. Grueneberg, Ph.D

NAME

703-412-7050

DIRECT PHONE #

OUR REFERENCE

209128US0  
09/870,496

YOUR REFERENCE

**MESSAGE**

PATENT, TRADEMARK AND COPYRIGHT LAW  
AND RELATED FEDERAL AND ITS LITIGATION  
WWW.OBLOM.COM

(703) 413-3000  
(703) 413-2220 FACSIMILE  
OBLOMPAT@OBLOM.COM

1840 DUKE STREET  
ALEXANDRIA, VIRGINIA 22314  
USA

ATTORNEYS AT LAW

Per our telephone discussion, attached are proposed amended claims  
for an Examiner's Amendment.

Unless otherwise indicated or obvious from the nature of the transmitted, the information contained in this facsimile message is attorney privileged and confidential information intended for the use of the individual or entity named above. If the reader of this message is not the intended recipient or the employee or agent responsible to deliver it to the intended recipient, you are hereby notified that any dissemination, distribution or copying of this communication is strictly prohibited. If you have received this communication in error or are not sure whether it is privileged, please immediately notify us by telephone and return the original message to us at the above address via the U.S. Postal Service at our Expense. Thank You.

Serial No. 09/870,496

209128US0

Proposed Amended Claims for Examiner's Amendment

Proposed  
DO NOT  
ENTER

Claim 17 (Withdrawn-Currently Amended): A magnetic disc, which comprises:  
an undercoat layer,  
a magnetic layer, and

a protective layer formed on a glass substrate as claimed in Claim 1, which consists  
essentially of, in terms of weight percent:

~~SiO<sub>2</sub> 40 to 59 %;~~

~~Al<sub>2</sub>O<sub>3</sub> 5 to 20 %;~~

~~B<sub>2</sub>O<sub>3</sub> 0 to 8 %;~~

~~MgO 0 to 10 %;~~

~~CaO 0 to 12 %;~~

~~SiO 2 to 20 %;~~

~~BaO 0 to 2 %;~~

~~ZnO 0 to 4 %;~~

~~Li<sub>2</sub>O 0 to 2 %;~~

~~Na<sub>2</sub>O 0 to 10 %;~~

~~K<sub>2</sub>O 0 to 12 %;~~

~~TiO<sub>2</sub> 0 to 10 %;~~ and

~~ZrO<sub>2</sub> 0 to 5 %;~~

~~wherein MgO + CaO + SiO + BaO is at least 15 %.~~

Claim 18 (Canceled):

Claim 19 (Withdrawn-Currently Amended): The ~~glass~~ substrate magnetic disk according to Claim 17, wherein  $\text{BaO} + \text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$  is at most 14 %.

Claim 20 (Withdrawn-Currently Amended): The ~~glass~~ substrate magnetic disk according to Claim 17, wherein  $\text{Li}_2\text{O} + \text{ZnO}$  is at most 2 %.

Claim 21 (Canceled):

Claim 22 (Canceled):

Claim 23 (Withdrawn-Currently Amended): A ~~glass~~ substrate made of the glass for a substrate magnetic disk as claimed in Claim 17, wherein the number of attachments having sizes of at least 10  $\mu\text{m}$  present on the surface of the glass substrate held in a steam atmosphere at 120° C under 2 atm for 20 hours, is not more than  $1/\text{cm}^2$ , ~~and the number of attachments having sizes ranging from 1  $\mu\text{m}$  to less than 10  $\mu\text{m}$  so present, is not more than  $10^5/\text{cm}^2$ .~~